



TROYCO
Global Industrial Supply

WhatsApp: 55-9185-7324, Tel: 55-9530-1503 eamglobal@aol.com

www.celoronybaquelita.mex.tl

TOLERANCIA DE ESPESOR DE LAMINADOS Y COMPOSITES (inch)

Espesor Nominal	Grado XX Baquelita	Grado C Celoron	Grado CE, CR, y A Celoron	Grado L Celoron	Grado LE Celoron	Grados de Vidrio G9, G-7, G-10, G-11
	+ / -					
0.010	0.002	--		0.003		0.002
0.015	0.0025			0.0035	0.0035	0.003
0.020	0.003			0.004	0.004	0.004
0.025	0.0035		0.005	0.0045	0.0045	0.0056
1/32	0.0035	0.0065	0.0065	0.005	0.005	0.0065
3/64	0.0045	0.0075	0.0075	0.006	0.006	0.0075
1/16	0.005	0.0075	0.0075	0.006	0.006	0.0075
3/32	0.007	0.009	0.009	0.007	0.007	0.009
1/8	0.008	0.009	0.009	0.007	0.007	0.009
5/32	0.009	0.011	0.011	0.010	0.010	0.015
3/16	0.010	0.0125	0.0125	0.010	0.010	0.019
7/32	0.011	0.014	0.014	0.011	0.011	0.021
1/4	0.012	0.030	0.015	0.024	0.012	0.022
5/16	0.0145	0.035	0.0175	0.029	0.0145	0.026
3/8	0.017	0.040	0.020	0.034	0.017	0.030
7/16	0.019	0.044	0.022	0.038	0.019	0.033
1/2	0.021	0.048	0.024	0.042	0.021	0.036
5/8	0.024	0.053	0.027	0.048	0.024	0.040
3/4	0.027	0.058	0.029	0.054	0.027	0.043
7/8	0.030	0.062	0.031	0.060	0.030	0.046
1	0.033	0.065	0.033	0.065	0.033	0.049
1-1/8	0.035	0.069	0.035	0.065	0.035	0.053
1-1/4	0.037	0.073	0.037	0.073	0.037	0.055
1-3/8	0.039	0.077	0.039	0.077	0.039	0.058
1-1/2	0.041	0.081	0.041	0.081	0.041	0.061
1-5/8	0.043	0.085	0.043	0.085	0.043	0.064
1-3/4	0.045	0.089	0.045	0.089	0.045	0.067
1-7/8	0.047	0.093	0.047	0.093	0.047	0.070
2	0.049	0.097	0.049	0.097	0.049	0.073
2-1/2						0.085
3						0.097

Tolerancia de Espesor en Hojas – Al menos el 90% de la hoja debera estar dentro de la tolerancia de espesor de la tabla anterior.